

RTV31, RTV60, RTV88

Silicone Rubber Compounds for High Temperature

Product Description RTV31, RTV60 and RTV88 silicone rubber compounds are high temperature two-part silicone elastomers. They are supplied ready-to-use with a base compound and DBT (dibutyl tin dilaurate) as the standard curing agent. DBT is suitable for most applications, however other catalysts are available to facilitate deep section cure, faster cure and automated mixing.
RTV31, RTV60 and RTV88 silicone rubber compounds differ primarily in viscosity in the uncured state.

- Key Performance Properties**
- Variable work times and cure rates by adjusting the amount and type of curing agent
 - Room temperature cure
 - Composition free of solvents and solvent odour
 - Excellent adhesion capabilities with primer
 - Excellent release properties
 - Retention of elastomeric properties at temperatures from -54°C up to 260°C continuously, and up to 316°C for short periods of time
 -

- Applications** Typical high temperature applications for these products include, but are not limited to:
- Potting and encapsulating electric motors and transformers
 - Fabrication of rubber parts
 - Casting moulds for low-melting point metals
 - Release applications such as rubber rollers
 - Thermal insulation

Typical Product Data

UNCURED PROPERTIES OF RTV BASE COMPOUNDS	RTV31	RTV60	RTV88
Colour	Red	Red	Red
Consistency	Pourable	Pourable	Spreadable Paste
Viscosity, mPa-s	25,000	47,000	880,000
Specific Gravity, g/cm ³	1.42	1.48	1.47
UNCURED PROPERTIES OF RTV BASE WITH 0.5% DBT CURING AGENT ADDED	RTV31	RTV60	RTV88
Work Time @ 25C, hrs	2	2	0.75
Cure Time @ 25C, hrs	24	24	24



CURED PROPERTIES (0.5 wt. % DBT Curing Agent added, cured 7 days at 25C and 50% R.H.)	RTV31	RTV60	RTV88
Mechanical			
Hardness, Shore A Durometer	54	57	58
Tensile Strength, MPa	6.0	7.0	6.0
Elongation, %	170	120	120
Tear Strength, kN/m	5.0	7.0	8.0
Shrinkage, %	0.6	0.6	0.6
Electrical			
Dielectric Strength, kV/mm (1.9 mm thick)	17.0	17.7	17.4
Dielectric Constant @ 1000 Hz	4.4	4	4.3
Dissipation Factor @ 1000 Hz	0.03	0.02	0.03
Volume Resistivity, ohm-cm	1.6×10^{14}	4.4×10^{14}	2.8×10^{14}

Thermal			
Useful Temperature Range, ° C	-54 to 260	-54 to 260	-54 to 260
Thermal Conductivity, W/m-K	0.31	0.31	0.31
Coefficient of Expansion, cm/cm, ° C	20×10^{-5}	20×10^{-5}	20×10^{-5}
Specific Heat, cal/gm, ° C	0.35	0.35	0.35

Specifications Typical product data values should not be used as specification. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV1 and RTV2.

Instructions for Use **Mixing**
Select a mixing container 4 to 5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out the RTV silicone rubber base compound and add the appropriate amount of curing agent. 0.5% DBT by weight will provide a work time or pot life of about one hour and a cure time of 24 hours. 0.5% DBT is the most commonly used concentration of curing agent for RTV31, RTV60 and RTV88 silicone rubber compounds. The pot life may be lengthened by using less DBT (as little as 0.1% DBT).

MEASURING GUIDE FOR CURING AGENT ADDITION

RTV Weight	Dibutyl Tin Dilaurate Concentration	
	0.1%	0.5%
100 grams	5 drops	25 drops
454 grams (1 lb.)	23 drops	115 drops (2.27 grams)

With clean tools, thoroughly mix the RTV base compound and the curing agent, scraping the sides and bottom of the container carefully to produce a homogeneous mixture. When using power mixers, avoid excessive speeds which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

Deaeration

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of 10-20 mbar. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. When using the RTV silicone rubber compound for potting, a deaeration step may be necessary after pouring to avoid capturing air in complex assemblies.

Curing

Using DBT curing agent at a level of 0.5%, these RTV silicone rubber compounds will cure in 24 hours at 25° C and 50% relative humidity to form durable, resilient rubbers. Under these conditions a pot life of about one hour will typically be available for pouring and working with the catalyzed material. Pot life may be increased by refrigerating the mixed material at 0° C after catalyzing. Cure times may be shortened by using mild heat up to 93° C maximum.

A choice of curing agents is available for use with RTV31, RTV60 and RTV88 silicone rubber compounds.

CuringAgent	Cure Speed	Curing Agent Concentration	Features
DBT	moderate	0.1-0.5%	standard
STO	fast	0.1-0.5%	small volume applications
RTV9811	moderate	5-10%	good deep section cure suitable for automatic mixing
RTV9950	moderate	5-10%	suitable for automatic mixing
RTV9910	slow	10%	suitable for automatic mixing

Deep Section Cure

If these RTV silicone rubber compounds are to be used in deep sections at temperatures over 150° C, the cured product should be properly conditioned prior to service. Following room temperature cure of 1-3 days, a typical program would be eight hours at 50° C intervals from 100° C to the service temperature. Longer times at each temperature will be required for larger parts or very deep sections.

Bonding

If adhesion is an important application requirement, RTV31, RTV60 and RTV88 silicone rubber compounds require a primer to bond to non-silicone surfaces. Thoroughly clean the substrate with a non-oily solvent such as naphtha or methyl ethyl ketone (MEK) and let dry. Then apply a uniform thin film of a suitable silicone primer such as SS4004P and SS4155 silicone primer and allow the primer to air dry for one hour or more. Finally, apply freshly catalyzed RTV silicone rubber compound to the primed surface and cure as recommended.

Handling and Safety

Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.

Storage and Warranty Period

The warranted shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers at following temperatures :

RTV 31 and RTV 60 : 2 – 10 °C
RTV88 : < -18 °C

Availability

RTV31/60/88 are available in 227 kg drums for which the catalyst needed has to be ordered separately. Further in 450 g, 5.5 kg and 23 kg containers all supplied with the DBT amount needed to catalyze the material. If other catalysts are desired for a specific application this should be ordered separately.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constância Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.225350	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	• Specialty Fluids	T 800.523.5862	F 304.746.1654
	• UA, Silanes, Resins, and Specialties	T 800.334.4674	F 304.746.1623
	• RTV Products-Elastomers	T 800.332.3390	F 304.746.1623
	• Sealants and Adhesives & Construction	T 877.943.7325	F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.5899.5135	F +52.55.5899.5138
	• Venezuela, Ecuador, Peru, Colombia, & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.225350	F +31.164.241750
	E cs-ap.silicones@momentive.com		
Pacific	• Japan	T +81.276.20.6182	
	• China	T +86.21.5050.4666 (ext. 1523)	
	• Korea	T +82.2.6201.4600	
	• Singapore	T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.