

SS4004P, SS4044P, SS4120, SS4155

Silicone Primers for use with One and Two-Component RTV Silicone Compounds

Product Description SS4004P, SS4044P, SS4120, and SS4155 primers are formulated for use with Momentive performance materials Silicones RTV silicone rubber adhesive sealants. Momentive performance materials Silicones one-component products offer primerless adhesion to many substrates. Primers are used to help promote adhesion to difficult-to-bond substrates. For most Momentive performance materials Silicones two-component products, a primer is required when an adhesive bond is needed between the silicone rubber compound and a non-silicone surface. All primers are one-component products and are supplied ready to use as pourable solvent solutions.

- Key Performance Properties**
- One component – no mixing
 - Simple handling procedures and equipment for easy use and low processing cost
 - Bright pink color of SS4004P primer and blue color of SS4155 primer permit easy visual determination of uniform films.
 - Transparency of SS4120 primer preserves visibility with colorless RTV615, RTV655, RTV6156, RTV6157, RTV6166, RTV6166, RTV6186, and RTV6196 products

Applications As indicated in the 'primer recommendation table', Momentive performance materials primers are recommended for use with specific two-component RTV silicone rubber compounds. The primers may be used to bond these silicone products to metals (such as aluminum, copper, steel, and stainless steel), ceramics, glass, some rigid plastics, and wood. Typically, adhesive strengths of 0.7 to 1.8 kN/m in a peel configuration and 1.4 to 4.2 MPa in lap shear may be developed.

Typical Product Data

Properties	SS4004P	SS4044P	SS4120	SS4155
Color	Pink	Clear	Clear, Colourless	Blue
Silicone Content, %	15	16	3	10
Specific Gravity	0.86	0.86	0.82	0.82
Solvents	Acetone Isopropanol Xylene N-butanol	Acetone Isopropanol Xylene N-butanol	Ethanol Methanol	Mineral Spirits
Dry Time, hrs.	1	1	1	1
Flash Point, °C	-12	-12	-0.5	37
D.O.T. Label	Flammable	Flammable	Flammable	Flammable

Specifications Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive Performance Materials Technical Service.

FDA STATUS

SS4044P and SS4120 primers can be used in food contact applications where FDA regulations apply.

Instructions for Use

All surfaces to be bonded should first be thoroughly cleaned with a suitable solvent such as naphtha or methyl ethyl ketone (MEK) to remove dirt, oil and grease. When practical, surfaces should be wiped dry before application of the primer coating. Abrasion of the surface will often improve adhesion. Primers may be applied by brushing, wiping, or dipping (spraying may sometimes produce erratic results). A thin, uniform primer coat of approximately 0.01 to 0.02 mm thickness usually provides the strongest bond. A drying time of one hour at room temperature is recommended prior to application of the RTV silicone rubber compound. On porous surfaces, a second coat of primer may be required. Allow at least one hour drying time between coats. For all of these silicone primers sufficient humidity must be available for proper drying. A minimum of 25% relative humidity is recommended for all but SS4155 primer for which a minimum of 40% is recommended. Formation of a chalky white haze indicates adequate drying of the SS4155 primer. Do not remove or contaminate such film prior to application of the RTV silicone rubber compound. All other primers are transparent after drying.

PRIMER RECOMMENDATION TABLE

RTV Silicone Rubber Compound	Primers Recommended	
	Primary	Alternates
RTV11 thru 88	SS4004P	SS4044P, SS4155
RTV500 series	SS4004P	SS4044P, SS4155
RTV615, 655	SS4120	SS4155
RTV627	SS4155	SS4120
RTV630	SS4155	SS4120
RTV6156, RTV6157	SS4120	SS4155
RTV6166,RTV6186,RTV6196,RTV8000 Series	SS4004P	SS4044P

Handling and Safety

Material Safety Data Sheets are available upon request from Momentive performance materials silicones. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.

Storage and Shelf Life

The shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers below 25° C. A slight white precipitate may form in storage. This should not impair performance of the primer. Do not shake the container prior to use, but carefully decant the clear primer from the top of the container as needed. A laboratory check of adhesion is suggested prior to product use.

Availability

SS4120 is available in 0.5L bottles
 SS4155 is available in 0.5L bottles, 20L pails, 200L drums
 SS4004P/4044P are available in 0.5L bottles and 200L drums



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constância Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.225350	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	• Specialty Fluids	T 800.523.5862	F 304.746.1654
	• UA, Silanes, Resins, and Specialties	T 800.334.4674	F 304.746.1623
	• RTV Products-Elastomers	T 800.332.3390	F 304.746.1623
	• Sealants and Adhesives & Construction	T 877.943.7325	F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.5899.5135	F +52.55.5899.5138
	• Venezuela, Ecuador, Peru, Colombia, & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.225350	F +31.164.241750
	E cs-ap.silicones@momentive.com		
Pacific	• Japan	T +81.276.20.6182	
	• China	T +86.21.5050.4666 (ext. 1523)	
	• Korea	T +82.2.6201.4600	
	• Singapore	T +65.6220.7022	
	Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.